

Our Ref.: 160-366
7MK-01S1468-1

U.S. PATENT APPLICATION

Inventor(s): Satoshi Okutsu
Kenichi Fujita
Yukio Kodama
Ichiro Toyoda
Yuji Hirasawa
Masashi Sawamura

Invention: COLORED COMPOSITION FOR COLOR FILTER AND COLOR FILTER

***NIXON & VANDERHYE P.C.
ATTORNEYS AT LAW
1100 NORTH GLEBE ROAD
8TH FLOOR
ARLINGTON, VIRGINIA 22201-4714
(703) 816-4000
Facsimile (703) 816-4100***

SPECIFICATION

TITLE OF THE INVENTION

COLORED COMPOSITION FOR COLOR FILTER AND COLOR FILTER

CROSS-REFERENCE TO RELATED APPLICATIONS

5 This application is based upon and claims the
benefit of priority from the prior Japanese Patent
Application No. 2000-390822, filed December 22, 2000,
the entire contents of which are incorporated herein by
reference.

BACKGROUND OF THE INVENTION

10 1. Field of the Invention

The present invention relates to a colored
composition for color filter used in a color liquid
crystal display device or a solid state image sensor,
and also to a color filter employing this colored
15 composition.

2. Description of the Related Art

A color filter is generally provided, on the
surface of a transparent substrate such as a glass
substrate, with at least two fine stripe-shaped filter
20 segments differing in hue from each other. These
filter segments are disposed parallel or intersected
with each other, or regularly arrayed vertically and
horizontally. Each filter segment is fine in width,
i.e., in the range of several micrometers to several
25 hundreds micrometers, and is arrayed regularly for each
hue.

On a color filter used in a color liquid crystal

display device, transparent electrodes for actuating
the liquid crystal are formed usually by means of vapor
deposition or sputtering. Further, an alignment film
for aligning the liquid crystal in a predetermined
5 direction is formed over the transparent electrodes.
In order to make the best use of the performances of
these transparent electrodes and alignment film, the
deposition of them is required to be performed at a
high temperature of usually 200°C or more, preferably
10 230°C or more.

Therefore, the manufacture of the color filter is
mainly performed at present by a method called a
pigment dispersion method wherein pigments, which are
excellent in light resistance and heat resistance, are
15 employed as a colorant. Specifically, a color filter
is now manufactured mainly by the following two
methods.

According to a first method, a dispersion of
pigment of a first color in a solution of a
20 photosensitive transparent resin is coated on the
surface of a transparent substrate such as a glass
substrate. The coated layer is dried to remove the
solvent, and then subjected to a patterning exposure,
followed by a developing process to remove the
25 unexposed portions, thus forming a pattern of the first
color. Subsequently, a processing such as a heat
treatment is applied to the first color pattern, if

required. Thereafter, the procedures similar to those described above are repeated successively for all of the remaining filter colors. In this way, a desired color filter is produced.

5 According to a second method, a dispersion of pigment of a first color in a solution of transparent resin is coated on the surface of transparent substrate such as glass substrate. The coated layer is dried to remove the solvent. A resist such as a positive resist
10 is coated on the surface of the coated layer, and subjected to a patterning exposure. Then, the resist layer is subjected to a developing process to form a resist pattern, which is used as an etching resist in the subsequent process wherein those portions of the
15 coated layer which are not covered by the resist pattern are removed with an etching solution. Thereafter, the resist pattern is removed to form a pattern of the first color. Subsequently, a processing such as a heat treatment is applied to the first color pattern,
20 if required. Thereafter, the procedures similar to those described above are repeated successively for all of the remaining filter colors. In this way, a desired color filter is produced. In this case, the developing of the resist and the etching of the coated layer may
25 be performed simultaneously.

 In the manufacture of green filter according to the aforementioned methods, a colored composition

containing halogenated copper phthalocyanine green pigment has been conventionally employed. 16 halogen atoms can be introduced into the phthalocyanine ring, and C.I. Pigment Green 7, in which only chlorine atoms are introduced as halogen atoms into the copper phthalocyanine, C.I. Pigment Green 36, in which chlorine and bromine atoms are introduced into the copper phthalocyanine, are known. Generally, the higher the content of bromine introduced into copper phthalocyanine is, the higher the tendency that the visible light-transmitting wavelength region is shifted toward a longer wavelength side. The brightness (Y value) among three stimulus values of XYZ color specification system can be enhanced when the light-transmitting wavelength region is shifted toward a longer wavelength side as far as the green filter of color filter is concerned. Thus, C.I. Pigment Green 36 is generally employed for a green color filter.

However, there is a limitation in the quantity of bromine (i.e., at most 16 bromine atoms) that can be introduced into copper phthalocyanine pigment. Nonetheless, there is a strong demand for a green colored composition that can provide a green filter whose light-transmitting wavelength region is further shifted toward a longer wavelength side to further improving the brightness.

Therefore, an object of the present invention is

to provide a colored composition for color filter,
which is capable of providing a green filter exhibiting
an improved brightness, and a color filter.

BRIEF SUMMARY OF THE INVENTION

5 The present inventors have made intensive studies
in an attempt to achieve the aforementioned object. As
a result, they have found that a combination of a
halogenated copper phthalocyanine pigment and a
halogenated metallophthalocyanine pigment having, as a
10 central metal, a specified metal other than copper at a
specified ratio can shift the light-transmitting
wavelength region toward a longer wavelength side, thus
making it possible to obtain a green filter exhibiting
a further increased brightness.

15 Thus, the present invention provides a green
colored composition for color filter, which comprises a
colorant carrier comprising a transparent resin, a
precursor of a transparent resin or a mixture thereof;
and a green colorant dispersed in the colorant carrier
20 and comprising at least one first halogenated
metallophthalocyanine pigment having copper as a
central metal, and at least one second halogenated
metallophthalocyanine pigment having, as a central
metal, a metal selected from the group consisting of
25 Mg, Al, Si, Ti, V, Mn, Fe, Co, Ni, Zn, Ge and Sn;
wherein the content of the second halogenated
metallophthalocyanine pigment is within a range of 1 to

80 mol% based on a total amount of the green colorant.

In the colored composition of the present invention, the first halogenated metallophthalocyanine pigment preferably contains 8 to 16 bromine atoms per molecule thereof.

Further, in the colored composition of the present invention, the second halogenated metallophthalocyanine pigment preferably contains 8 to 16 bromine atoms per molecule thereof.

According to a second aspect of the invention, there is provided a color filter comprising at least one red filter segment, at least one blue filter segment, and at least one green filter segment, wherein at least one green filter segment is prepared from a colored composition of the present invention.

Additional objects and advantages of the invention will be set forth in the description which follows, and in part will be obvious from the description, or may be learned by practice of the invention. The objects and advantages of the invention may be realized and obtained by means of the instrumentalities and combinations particularly pointed out hereinafter.

DETAILED DESCRIPTION OF THE INVENTION

The colored composition according to the present invention contains a colorant carrier formed of a transparent resin, a precursor of a transparent resin or a mixture thereof, and a green colorant dispersed in

the colorant carrier. The green colorant comprises a first halogenated metallophthalocyanine pigment having copper as a central metal, and a second halogenated metallophthalocyanine pigment having, as a central metal, a specified metal other than copper. The colorant carrier provides a resinous binder in a finished green filter segments.

Specific examples of the first halogenated metallophthalocyanine pigment, i.e., halogenated copper phthalocyanine pigment, employed in the present invention include C.I. Pigment Green 7 wherein only chlorine atoms are introduced therein as halogen atoms, and C.I. Pigment Green 36 wherein chlorine and bromine atoms are introduced therein as halogen atoms.

Among them, a halogenated copper phthalocyanine pigment incorporating bromine therein, e.g., C.I. Pigment Green 36 can be preferably employed, since the transmitting wavelength region is shifted to a longer wavelength side. Further, in order to enable the transmitting wavelength region of halogenated copper phthalocyanine pigment to be shifted to a longer wavelength side, the halogenated copper phthalocyanine pigment preferably contains 8 to 16 bromine atoms, more preferably 12 to 16 bromine atoms, per molecule, on average.

The second halogenated metallophthalocyanine pigment constituting the green pigment together with

the halogenated copper phthalocyanine pigment functions to shift the transmitting wavelength region of green filter segment toward a further longer wavelength side.

The central metal of the second halogenated

5 metallophthalocyanine pigment is at least one metal (hereinafter referred to as specified dissimilar metal) selected from the group consisting of Mg, Al, Si, Ti, V, Mn, Fe, Co, Ni, Zn, Ge and Sn. These second halogenated metallophthalocyanine pigments may be used
10 in combination wherein the central metals differ from each other. Where the central metal is constituted by a trivalent or tetravalent metal such as Al, Si, Ti, V, Mn, Fe, Ge or Sn, an axial substituent(s) or axial ligand(s) may exist. Specific examples of such axial
15 substituents include, but not limited thereto, a halogen such as -F, -Cl, -Br or -I, alkoxyl group; phenoxy group, and =O.

In the present invention, the second halogenated metallophthalocyanine pigment is present in an amount
20 of 1 to 80 mol%, preferably 5 to 60 mol%, more preferably 9 to 45 mol% based on the total amount of the green colorant (the first halogenated metallophthalocyanine pigment (i.e. halogenated copper phthalocyanine pigment) + the second halogenated
25 metallophthalocyanine pigment). If an amount of the second halogenated metallophthalocyanine pigment is less than 1 mol%, the transmitting wavelength region is

difficult to shift to a longer wavelength side. On the other hand, if an amount of the second halogenated metallophthalocyanine pigment exceeds 80 mol%, the concentration of green color would become lower, thus deteriorating the chromaticity of green color, and is unsuited for use in the present invention, though the transmitting wavelength region is shifted to a longer wavelength side.

The green colorant employed in the present invention can be produced, for example, by a method wherein a crude metallophthalocyanine pigment having the specified dissimilar metal as a central metal is halogenated by a known method to obtain a halogenated pigment, which is mixed with a crude halogenated copper phthalocyanine pigment. Alternatively, the green colorant can be prepared by a method wherein a crude copper phthalocyanine pigment is halogenated in the presence of a specified dissimilar metal compound to synthesize a crude halogenated (copper/specified dissimilar metal) phthalocyanine pigment in which a part of coppers is replaced by the specified dissimilar metal. Also, the green colorant can be prepared by a method wherein part of coppers of the crude halogenated copper phthalocyanine pigment is replaced by the specified dissimilar metal.

Since the crude halogenated (copper/specified dissimilar metal) phthalocyanine pigment obtained

according to the aforementioned methods is nearly amorphous in particle configuration, it would be difficult to disperse in the carrier. Therefore, the crude pigment should preferably be allowed to be
5 crystal-grown by means of a conventional method. The crystal growth can be effected by a method wherein the above amorphous crude halogenated (copper/specified dissimilar metal) phthalocyanine pigment is dispersed in an organic solvent and then heated, or by a method
10 wherein the phthalocyanine pigment is heated while imparting a mechanical shear to the phthalocyanine pigment (hereinafter, these methods are referred to as pigmentization process).

More specifically, one example of the former
15 pigmentization processes involves mixing an amorphous crude halogenated (copper/specified dissimilar metal) phthalocyanine pigment with about 5 to 30 times weight of xylene, and growing crystals by heating the mixture under the reflux of xylene while stirring. On the
20 other hand, one example of the latter pigmentization processes is a called salt milling process wherein a mixture of an amorphous crude halogenated (copper/specified dissimilar metal) phthalocyanine pigment, a water-soluble inorganic salt and a small
25 amount of a water-soluble organic solvent is kneaded using a kneader while heating the mixture, thereby enabling the crystal growth of the pigment to proceed.

However, care should preferably be taken not to grow crystals excessively largely, since the color filter is required to be excellent in transparency. The average particle diameter of the primary particles of the pigment crystal obtained should preferably be not more than 0.1 μm , more preferably not more than 0.05 μm .

As a solvent used in the pigmentization processes, use may be made of, other than xylene as mentioned above, a hydrocarbon solvent such as toluene, ethyl benzene, diethyl benzene, methyl cyclohexane or ethyl cyclohexane; a halogenated hydrocarbon solvent such as trichloroethane, tetrachloroethane, trichloropropane, monochlorobenzene, dichlorobenzene, trichlorobenzene or chlorotoluene; an alcoholic solvent such as butanol, isopentanol, hexanol, 2-ethyl-1-hexanol, benzyl alcohol, cyclohexanol, ethylene glycol or propylene glycol; a phenolic solvent such as phenol or cresol; an ether solvent such as dibutyl ether, anisole, dioxane, ethylene glycol diethyl ether or ethylene glycol dibutyl ether; a ketone solvent such as butyl methyl ketone, isobutyl ketone, cyclohexanone, methylcyclohexanone or acetophenone; an ester solvent such as propyl acetate, butyl acetate, isobutyl acetate, isopentyl acetate, 3-methoxybutyl acetate, 2-ethylbutyl acetate, 2-ethylhexyl acetate, butyl propionate, ethyl benzoate, diethyl maleate or ethylene glycol monoacetate; nitrobenzene; N-methyl aniline;

pyperidine; pyridine; N,N-dimethylformamide; N-methyl-
2-pyrrolidone; ethyl cellosolve; butyl cellosolve;
ethyl carbitol. These solvents can be employed singly
or in combination. Further, it is possible to employ
5 an emulsion in which a water-insoluble solvent is
emulsified or dispersed in water using a surfactant.

The salt milling process mentioned above is a
pigmentization process wherein a crude pigment, a
water-soluble inorganic salt and a water-soluble
10 organic solvent are mixed together and kneaded under
heating, followed by removing the inorganic salt and a
high-boiling point solvent by washing with water. The
water-soluble inorganic salt functions as a grinding
aid, and by taking advantage of the high hardness of
15 the inorganic salt, the crude pigment is pulverized.
It is thought that the pulverization causes the
generation of active surfaces, which give rise to the
crystal growth of the pigment. Therefore, the grinding
and crystal growth of the crude pigment occur
20 concurrently during kneading, and the primary particle
diameter of the pigment varies depending on the
conditions of the kneading step. When the
pigmentization process is performed through the salt
milling, the crystal growth should be promoted by the
25 heating of the crude pigment. The heating temperature
is preferably 70 to 150°C. If a heating temperature is
less than 70°C, the crystal growth would become

insufficient, so that the configuration of the particles of pigment would become nearly amorphous, which is undesirable. On the other hand, if a heating temperature exceeds 150°C, the crystal growth would
5 become excessive, thus excessively enlarging the primary particle diameter of the pigment, which is not suitable as a colorant for a colored composition for color filter.

The water-soluble inorganic salt employed in the
10 salt milling process includes sodium chloride, barium chloride, potassium chloride and sodium sulfate. Among them, the employment of sodium chloride is preferable in terms of cost. The quantity of the inorganic salt employed in the salt milling should preferably be 0.5
15 to 20 times weight, more preferably 1 to 10 times weight as much as that of the crude pigment, in view of the treatment efficiency and of productivity efficiency.

The water-soluble organic solvent serves to wet
20 the crude pigment and the water-soluble inorganic salt. Use may be made of any water-soluble organic solvent, which can be dissolved in (or miscible with) water and which does not substantially dissolve the inorganic salt used. However, during the salt milling process,
25 the temperature is increased to provide a condition under which a solvent is ready to evaporate. Thus, the solvent used preferably have a boiling point of as high

as not less than 120°C in view of safety. Specific examples of such water-soluble organic solvent include, for example, 2-methoxy ethanol, 2-butoxy ethanol, 2-(isopentyloxy)ethanol, 2-(hexyloxy)ethanol, diethylene glycol, diethylene glycol monoethyl ether, diethylene glycol monobutyl ether, triethylene glycol, triethylene glycol monomethyl ether, liquid polyethylene glycol, 1-methoxy-2-propanol, 1-ethoxy-2-propanol, dipropylene glycol, dipropylene glycol monomethyl ether, dipropylene glycol monoethyl ether and liquid polypropylene glycol.

In order to prevent the pigment obtained through the pigmentization process from being agglomerated during the drying process of the pigment, a resin may be co-used so as to enable the pigment to be easily dispersed in the transparent resin. When a resin is co-used during salt milling process, a soft powdery pigment can be obtained. A resin used in the salt milling process is preferably one that is solid at room temperature, water-insoluble and soluble at least partially in the aforementioned organic solvent. Such a resin includes a natural resin, a modified natural resin, a synthetic resin and a synthetic resin modified with a natural resin. One typical example of the natural resin is rosin. The modified natural resin includes a rosin derivative, a cellulose derivative, a rubber derivative, a protein derivative, and an

oligomer thereof. The synthetic resin includes an epoxy resin, an acrylic resin, a maleic resin, a butyral resin, a polyester resin, a melamine resin, a phenolic resin, a polyurethane resin, and a polyamide resin. The synthetic resin modified with a natural resin includes a rosin-modified maleic resin, and a rosin-modified phenolic resin. The resin can be preferably employed at a ratio ranging from 5 to 100% by weight based on the crude pigment used.

In addition to the aforementioned resin, it is also possible, in the salt milling process, to add an additive such as a dispersing agent or a plasticizer; or an inorganic pigment which is generally known as an extender pigment such as calcium carbonate, barium sulfate or silica. It is also possible to add, in the salt milling process, other kinds of pigment in order to adjust the resultant hue.

The colorant carrier for dispersing the green colorant of the present invention can be constituted as mentioned above by a transparent resin, a precursor of a transparent resin, or a mixture thereof. The transparent resin preferably exhibits a light transmittance of not less than 80%, more preferably not less than 95% in the entire wavelength region of the visible light region ranging from 400 to 700 nm in wavelength. The transparent resin may be a thermoplastic resin, a thermosetting resin or a

photosensitive resin. The precursor of the transparent resin includes a monomer or oligomer which is capable of producing a transparent resin when cured by the irradiation of radiation. These transparent resin and precursor may be employed singly or in combination of two or more of them.

If the green colored composition according to the present invention is cured by the irradiation of ultraviolet rays, a photo-initiator is added to the composition.

The transparent thermoplastic resin includes a butyral resin, a styrene-maleic acid copolymer, a chlorinated polyethylene, a chlorinated polypropylene, a polyvinyl chloride, a vinyl chloride-vinyl acetate copolymer, a polyvinyl acetate, a polyurethane resin, a phenol resin, a polyester resin, an acrylic resin, an alkyd resin, a styrene resin, a polyamide resin, a rubber-based resin, a cyclized rubber, a cellulose, a polybutadiene, and a polyimide resin. Further, the thermosetting resin includes an epoxy resin, a benzoguanamine resin, a melamine resin, and a urea resin.

The photo-sensitive resin includes reaction products of linear polymers having a reactive substituent group such as hydroxyl group, carboxyl group and/or amino group with a compound, e.g., (meth)acrylic compound or cinnamic acid having a

reactive substituent such as isocyanate group, aldehyde group and/or epoxy group to introduce a photo-crosslinkable group such as (meth)acryloyl group and/or styryl group in the linear polymers. It is also possible to employ, as a photo-sensitive resin, a half-esterified product of a linear polymer containing an acid anhydride such as styrene-maleic anhydride copolymer or α -olefin-maleic anhydride copolymer with a (meth)acrylic compound having hydroxyl group such as hydroxyalkyl (meth)acrylate.

The monomer and oligomer include acrylic esters and methacrylic esters such as 2-hydroxyethyl (meth)acrylate, 2-hydroxypropyl (meth)acrylate, cyclohexyl (meth)acrylate, polyethylene glycol di(meth)acrylate, pentaerythritol tri(meth)acrylate, dipentaerythritol hexa(meth)acrylate, tricyclodecanyl (meth)acrylate, melamine (meth)acrylate, epoxy (meth)acrylate, etc.; (meth)acrylic acid; styrene; vinyl acetate; (meth)acryl amide; N-hydroxymethyl (meth)acryl amide; and acrylonitrile.

Specific examples of the photo-initiator include acetophenone-based photo-initiators such as 4-phenoxydichloroacetophenone, 4-*t*-butyl-dichloroacetophenone, diethoxyacetophenone, 1-(4-isopropylphenyl)-2-hydroxy-2-methylpropan-1-one, 1-hydroxycyclohexylphenyl ketone,

2-benzyl-2-dimethylamino-1-(4-morpholinophenyl)-butan-
1-one, etc.; benzoin-based photo-initiators such as
benzoin, benzoinmethyl ether, benzoinethyl ether,
benzoinisopropyl ether, benzyldimethyl ketal, etc.;

5 benzophenone-based photo-initiators such as
benzophenone, benzoyl benzoic acid, methyl
benzoylbenzoate, 4-phenyl benzophenone,
hydroxybenzophenone, acrylic benzophenone, 4-benzoyl-
4'-methyldiphenyl sulfide, etc.; thioxanthone-based

10 photo-initiators such as thioxanthone, 2-
chlorothioxanthone, 2-methylthioxanthone,
isopropylthioxanthone, 2,4-diisopropylthioxanthone,
etc.; triazine-based photo-initiators such as 2,4,6-
trichloro-s-triazine, 2-phenyl-4,6-

15 bis(trichloromethyl)-s-triazine, 2-(p-methoxyphenyl)-
4,6-bis(trichloromethyl)-s-triazine, 2-(p-tolyl)-4,6-
bis(trichloromethyl)-s-triazine, 2-pipenyl-4,6-
bis(trichloromethyl)-s-triazine, 2,4-
bis(trichloromethyl)-6-styryl-s-triazine, 2-(naphtho-1-

20 yl)-4,6-bis(trichloromethyl)-s-triazine, 2-(4-methoxy-
naphtho-1-yl)-4,6-bis(trichloromethyl)-s-triazine, 2,4-
trichloromethyl-(piperonyl)-6-triazine, 2,4-
trichloromethyl-(4'-methoxystyryl)-6-triazine, etc.;

borate-based photo-initiators; carbazole-based photo-

25 initiators; and imidazole-based photo-initiators.

The aforementioned photo-initiators can be
employed singly or in combination of two or more kinds,

and may be also used together with a sensitizer such as α -acyloxim ester, acylphosphine oxide, methylphenyl glyoxylate, benzyl, 9,10-phenanthrene quinone, camphor quinone, ethylanthraquinone, 4,4'-

5 diethylisophthalophenone, 3,3',4,4'-tetra(t-butyl peroxy carbonyl)benzophenone, and 4,4'-diethyl aminobenzophenone.

The colored composition according to the present invention can be manufactured by a process wherein a
10 green colorant consisting of a halogenated copper phthalocyanine pigment and a second halogenated metallophthalocyanine pigment are finely dispersed, if required, together with any of the aforementioned photo-initiators, in a colorant carrier by using
15 various dispersing means such as a triple roll mill, a dual roll mill, a sand mill or a kneader. Alternatively, the colored composition according to the present invention can be manufactured by a process wherein a halogenated copper phthalocyanine pigment and
20 a second halogenated metallophthalocyanine pigment are separately dispersed in a colorant carrier, and then, both of the resultant dispersions are mixed together at a ratio which makes the content of the second halogenated metallophthalocyanine pigment become the
25 aforementioned predetermined ratio.

In dispersing the pigment in a colorant carrier, it is possible to optionally employ a dispersing aid

such as a resin-type pigment dispersant, a surfactant or a dyestuff derivative or pigment derivative. Since this dispersing aid is very useful for dispersing a pigment as well as for preventing the pigment thus dispersed from being reaggregated, if this dispersing agent is employed in dispersing a pigment in a colorant carrier, it would become possible to obtain a color filter which is excellent in transparency.

The resin-type pigment dispersant has a pigment-affinity moiety which is adsorbable onto a pigment, and a moiety which is compatible with a colorant carrier, and functions to stably disperse the pigment in the colorant carrier by being adsorbed on the pigment. Specific examples of the resin-type pigment dispersant include a polyurethane, a polycarboxylate such as polyacrylate, an unsaturated polyamide, a polycarboxylic acid, a (partial) amine salt of a polycarboxylic acid, an ammonium salt of a polycarboxylic acid, an alkylamine salt of a polycarboxylic acid, a polysiloxane, a long chain polyaminoamide phosphate, a hydroxyl-containing polycarbonate, modified materials thereof, an oil dispersant such as an amide which can be formed through a reaction between a poly(lower alkylene imine) and a polyester having a free carboxyl group or salts of the amide, a water-soluble resin or water soluble polymer such as a (meth)acrylic acid-styrene copolymer, a

(meth)acrylic acid-(meth)acrylate copolymer, a styrene-
maleic acid copolymer, a polyvinyl alcohol or a
poly(vinyl pyrrolidone); a polyester, a modified
polyacrylate, an ethylene oxide/propylene oxide addi-
5 tion compound, and phosphate. These compounds can be
employed singly or in combination of two or more kinds.

The surfactant includes anionic surfactants such
as sodium lauryl sulfate, polyoxyethylene alkylether
sulfate, sodium dodecylbenzene sulfonate, alkali salt
10 of styrene-acrylic acid copolymer, sodium stearate,
sodium alkylnaphthalene sulfonate, sodium alkyldiphenyl
ether disulfonate, monoethanol amine lauryl sulfate,
triethanol amine lauryl sulfate, ammonium lauryl
sulfate, monoethanol amine stearate, monoethanol amine
15 of styrene-acrylic acid copolymer, polyoxyethylene
alkylether phosphate; nonionic surfactants such as
polyoxyethylene oleyl ether, polyoxyethylene lauryl
ether, polyoxyethylene nonylphenyl ether,
polyoxyethylene alkylether phosphate, polyoxyethylene
20 sorbitan monostearate, polyethylene glycol monolaurate,
etc.; cationic surfactants such as alkyl quaternary
ammonium salt or ethylene oxide addition compounds
thereof, etc.; and amphoteric surfactants such as alkyl
betaine such as betaine alkyldimethyl aminoacetate, and
25 alkyl imidazoline. These compounds can be employed
singly or in combination of two or more kinds.

The dyestuff or pigment derivative is a compound

consisting of an organic dyestuff into which a
substituent group is introduced. The dyestuff or
pigment derivative to be employed in the present
invention should preferably be green or yellow in color
5 in view of the hue of colored composition. However, if
the quantity required to be added is minimal, a
dyestuff derivative having blue color may be employed.
The dyestuff or pigment is defined herein to include a
light yellow aromatic polycyclic compound such as
10 naphthalene-based or anthraquinone-based compounds
which are not called dyestuff in general. As for this
dyestuff or pigment derivative, it is possible to
employ those described in Jpn. Pat. Appln. KOKAI
Publication No. 63-305173; Jpn. Pat. Appln. KOKOKU
15 Publication No. 57-15620; Jpn. Pat. Appln. KOKOKU
Publication No. 59-40172; Jpn. Pat. Appln. KOKOKU
Publication No. 63-17102; and Jpn. Pat. Appln. KOKOKU
Publication No. 5-9469. These dyestuff or pigment
derivatives can be employed singly or in combination of
20 two or more kinds.

The colored composition according to the present
invention preferably contains a yellow pigment in order
to realize a spectrum which is required for a green
filter. Although there is not any particular
25 limitation on this yellow pigment, it is preferably
selected from pigments which meet the spectrum required
and are excellent in various resistance properties.

Specific examples thereof include C.I. Pigment Yellow
1, 2, 3, 4, 5, 6, 10, 12, 13, 14, 15, 16, 17, 18, 24,
31, 32, 34, 35, 35:1, 36, 36:1, 37, 37:1, 40, 42, 43,
53, 55, 60, 61, 62, 63, 65, 73, 74, 77, 81, 83, 93, 94,
5 95, 97, 98, 100, 101, 104, 106, 108, 109, 110, 113,
114, 115, 116, 117, 118, 119, 120, 126, 127, 128, 129,
138, 139, 150, 151, 152, 153, 154, 155, 156, 161, 162,
164, 166, 168, 169, 170, 171, 172, 173, 174, 175, 176,
177, 179, 180, 181, 182, 185, 187, 199, etc.

10 These compounds can be employed singly or in
combination of two or more kinds. The yellow pigment
can be singly dispersed in a colorant carrier so as to
prepare a yellow color composition, can be mixed with a
green color composition wherein the aforementioned
15 green colorant is dispersed in a colorant carrier, or
can be mixed with the aforementioned green colorant and
dispersed in a colorant carrier.

 The colored composition for color filter according
to the present invention may contain a solvent for
20 enabling a pigment to be sufficiently dispersed in a
colorant carrier, thereby permitting the colored
composition to be easily coated on a transparent
substrate such as a glass substrate so as to form a
green filter segment having a dry film thickness of 0.2
25 to 5 μm . Specific examples of the solvent useful in
this case include cyclohexanone, ethyl Cellosolve
acetate, butyl Cellosolve acetate, 1-methoxy-2-propyl

acetate, diethyleneglycol dimethyl ether, ethyl
benzene, ethyleneglycol diethyl ether, xylene, ethyl
Cellosolve, methyl-n-amyl ketone, propyleneglycol
monomethylether, toluene, methylethyl ketone, ethyl
5 acetate, methanol, ethanol, isopropyl alcohol, butanol,
isobutyl ketone, petroleum-based solvents, etc. These
solvents may be employed singly or in combination
thereof.

The colored composition for color filter according
10 to the present invention may contain a storage
stabilizer for stabilizing the time viscosity of the
composition. Specific examples of such a storage
stabilizer include benzyltrimethyl chloride, a
quaternary ammonium chloride such as diethylhydroxy
15 amine; an organic acid such as lactic acid, oxalic acid
and a methyl ether thereof; t-butylpyrocatechol; an
organic phosphine such as tetraethyl phosphine or
tetraphenyl phosphine; phosphite; etc.

The colored composition for color filter according
20 to the present invention can be formulated as a
printing ink for gravure offset, a printing ink for
water-less offset, a printing ink for silk screen
printing, or a solvent development type or alkali
development type coloring resist material. The
25 coloring resist material can be manufactured by
dispersing the green colorant of the present invention
in a composition comprising a monomer, a

photo-initiator, and a resin selected from the group consisting of a thermoplastic resin, a thermosetting resin and a photo-sensitive resin.

5 The green colorant of the present invention and the yellow pigment employed as required can be incorporated in the colored composition of the present invention in an amount of 1.5 to 7% by weight in total (green colorant + yellow pigment) if the green filter segment is formed by means of photolithography, or in 10 an amount of 1.5 to 55% by weight in total (green colorant + yellow pigment) if the green filter segment is formed by means of printing method. In any case, the pigments (green colorant + yellow pigment) can be incorporated in the final green filter segment in an 15 amount of preferably 10 to 40% by weight, more preferably 20 to 50% by weight (the balance of the colored composition being constituted substantially by a resinous binder provided by a colorant carrier). The weight ratio between the green colorant and the yellow 20 pigment is preferably 1 : 1 to 2.5 : 1. Accordingly, the amount of the green colorant contained in the final green filter segment is preferably 5% by weight to 39% by weight.

25 The green colored composition according to the present invention is preferably subjected to a centrifugal separation or a filtering using a sintered filter or a membrane filter before use so as to remove

coarse particles having a particle diameter of 5 μm or more, more preferably 1 μm or more, most preferably 0.5 μm or more and the dusts that have been intermingled therein.

5 As already described above, the color filter according to the present invention comprises at least one red filter segment, at least one blue filter segment, and at least one green filter segment. In this case, the green filter segment is formed using a colored composition of the present invention. The red
10 filter segment and the blue filter segment can be formed by making use of an ordinary red color composition and an ordinary blue color composition, respectively.

15 The red colored composition may be a composition that can be obtained by substituting a red pigment for the green colorant in the colored composition of the present invention. Specific examples of the red pigment include C.I. Pigment Red 7, 14, 41, 48:1, 48:2,
20 48:3, 48:4, 146, 177, 178, 184, 185, 187, 200, 202, 208, 210, 246, 254, 255, 264, 272, etc.

 The blue colored composition may a composition that can be obtained by substituting a blue pigment for the green colorant in the colored composition of the present invention and by making use of a violet pigment
25 or the aforementioned yellow pigments as a toning colorant if required, the blue pigment being selected

for example from C.I. Pigment Blue 15, 15:1, 15:2, 15:3, 15:4, 15:6, 16, 60, etc., and the violet pigment being selected for example from C.I. Pigment Violet 19, 23, 27, 32, 42, etc.

5 The color filter according to the present invention can be manufactured by forming each filter segment on a transparent substrate using the colored compositions including the colored composition of the present invention by means of a printing method or a
10 photolithography.

 As the transparent substrate, it is possible to employ a glass substrate or a plastic substrate formed of a resin such as a polycarbonate, a polymethylmethacrylate or a polyethylene terephthalate.

15 The formation of each color filter segment by means of a printing method is advantageous in that since the patterning of the filter segment can be achieved by simply repeating the printing and drying processes of a colored composition prepared as a
20 printing ink for each color, the color filter can be manufactured at low cost and with excellent mass-productivity. Additionally, owing to the development of printing technique in recent years, it is now possible to perform a printing of fine pattern which is
25 excellent in dimensional precision and also in flatness.

 For the purpose of printing, the ink composition

should preferably be formulated such that the ink can be hardly dried or cured on the form plate or on the blanket. Further, the controlling of the fluidity of ink on the printing machine is also important. In this regard, the adjustment of viscosity of ink can be performed by making use of a dispersant or an extender pigment.

If each color filter segment is to be formed by means of a photolithography, a colored composition which has been formulated into a solvent development type or alkali development type coloring resist material is coated on a transparent substrate to a thickness of 0.2 to 5 μm (dry thickness) by means of coating method such as spray coating, spin coating, slit coating or roll coating to form a film. After being dried if required, the film is exposed to ultraviolet ray through a mask having a predetermined pattern and disposed in contact with or non-contacted with the film. Thereafter, the film is dipped in a solvent or an alkaline developing solution or sprayed with a solvent or a developing solution so as to remove the unexposed portion or uncured portion of the film, thereby forming a desired pattern. The same procedures are repeated for the formation of pattern of other colors, thereby manufacturing the color filter. In these procedures, heating may be applied thereto for the purpose of promoting the polymerization of the

coloring resist material. According to this
photolithography, it is possible to manufacture a color
filter which is more excellent in precision than that
to be obtained by means of the aforementioned printing
method.

An aqueous solution of sodium carbonate or sodium
hydroxide may be employed as an alkaline developing
solution on the occasion of development. It is also
possible to employ an organic alkali such as
dimethylbenzylamine, triethanolamine, etc. on the
occasion of development. It is also possible to
incorporate an antifoaming agent or a surfactant into
the developing solution.

After the coating and drying of the coloring
resist material, a film which is capable of preventing
oxygen-induced polymerization inhibition for the
purpose of improving the sensitivity of the film to
ultraviolet ray may be deposited thereon by the coating
and drying of a water-soluble or alkali-soluble resin
such as polyvinyl alcohol or a water-soluble acrylic
resin before the irradiation with ultraviolet ray.

The color filter of the present invention can be
manufactured also by means of electrodeposition method
or transferring method other than the aforementioned
methods. In this regard, the colored composition of
the present invention is also applicable to any of
these methods. By the way, the electrodeposition

method is a method wherein each color filter segment is electrodeposited on the surface of a transparent electroconductive film through the electrophoresis of colloid particles by taking advantage of the transparent electroconductive film formed in advance on the transparent substrate. Whereas, the transferring method is a method wherein a color filter layer is formed in advance on the surface of releasable transferring base sheet, and then, this color filter layer is transferred onto a desired transparent substrate.

Next, the present invention will be further explained with reference to the following examples, which are not intended to limit the scope of the present invention. In the Examples given below, all "part(s)" are by weight, and all "%" means "mol %".

First of all, the acrylic resin solution, the crude green pigment and the green pigment which were employed in the following examples and comparative examples will be explained.

<Preparation of an acrylic resin solution>

800 parts of cyclohexanone were introduced into a reaction vessel and heated at a temperature of 100°C while injecting nitrogen gas into the reaction vessel, and a mixture consisting of the monomers described below and a thermal polymerization initiator was added dropwise over one hour at a temperature of 100°C,

thereby performing the polymerization reaction thereof.

	Styrene	60.0 parts
	Methacrylic acid	60.0 parts
	Methyl methacrylate	65.0 parts
5	Butyl methacrylate	65.0 parts
	Azobisisobutyronitrile	10.0 parts

Upon finishing the dropwise addition of the mixture, the mixture was allowed to further react for 3 hours. Then, 2.0 parts of azobisisobutyronitrile dissolved in 50 parts of cyclohexanone were added to the reaction mixture, and the resultant mixture was allowed to proceed the reaction thereof at a temperature of 100°C for one hour to obtain a solution of acrylic resin having a weight average molecular weight of about 40000.

After being cooled down to room temperature, about 2g of the resin solution thus obtained was sampled and heat-dried for 20 minutes at a temperature of 180°C to thereby measure the nonvolatile matter thereof. Based on this measurement, cyclohexanone was added to the solution of acrylic resin that had been synthesized previously so as to prepare a solution of acrylic resin containing 20% by weight of the nonvolatile matter.

Next, the method of synthesizing the crude green pigment will be described. By the way, the measurement of metals in the crude pigment synthesized was performed as follows. First, 0.5g of crude pigment,

1 mL of sulfuric acid and 3 mL of nitric acid were placed in a 100 mL beaker, and heated for one and half hours over a gas stove to decompose the crude pigment, which was followed by another heating treatment in an electric furnace heated to a temperature of 600°C for 4 hours to further decompose the crude pigment. 5 mL of hydrochloric acid and 25 mL of pure water were added to the resultant decomposition product to dissolve the decomposition product. The resultant dissolved matter was formulated into a 50 mL solution, which was then subjected to ICP atomic emission spectrometry to measure the atomic weight of metals. The number of chlorine atom and of bromine atom in the crude pigment (an average number of chlorine atom and of bromine atom in one molecule) was measured by a method wherein 0.01g of the crude pigment was wrapped in a sheet of No. 6 filter paper, and 5 drops of hydrogen peroxide was added dropwise onto this filter paper to obtain a test sample, which was then burned in a combustion flask purged with oxygen gas to obtain a residue product, which was formulated into a 100 mL solution and subjected to ion chromatography to measure the number of chlorine atom and of bromine atom.

<Crude green pigment 1>

64 parts of copper phthalocyanine and 5 parts of aluminum phthalocyanine were dissolved in a fused salt mixture which was heated in advance to 140°C, the fused

salt mixture comprising 429 parts of aluminum chloride and 96 parts of sodium chloride, thereby obtaining a mixture, which was then stirred for 2 hours while maintaining the aforementioned temperature. Then, the

5 reaction temperature of the mixture was increased to 180°C, and bromine was added dropwise in the reaction mixture at a rate of 48 parts per hour over 5 hours. Subsequently, chlorine was introduced in the reaction mixture at a rate of 30 parts per hour over 2 hours.

10 The resultant reaction solution was slowly poured into 4000 parts of water and then, subjected to filtration and water-washing to obtain 197.2 parts of crude green pigment 1. The crude green pigment 1 thus obtained was found to consist of 90.5% of crude halogenated copper

15 phthalocyanine pigment and 9.5% of crude halogenated aluminum phthalocyanine pigment, wherein the crude halogenated copper phthalocyanine pigment contained in its each molecule bromine atom and chlorine atom in average number of 13.5 and 2.5, respectively, whereas

20 the crude halogenated aluminum phthalocyanine pigment contained in its each molecule bromine atom and chlorine atom in average number of 13.5 and 2.5, respectively.

<Crude green pigment 2>

25 69 parts of copper phthalocyanine were dissolved in a fused salt mixture which was heated in advance to 160°C, the fused salt mixture comprising 429 parts of

aluminum chloride and 96 parts of sodium chloride,
thereby obtaining a mixture, which was then stirred for
2 hours at an increased temperature 200°C. Then, the
reaction temperature of the mixture was lowered down to
5 180°C, and bromine was added dropwise in the reaction
mixture at a rate of 48 parts per hour over 5 hours.
Subsequently, chlorine was introduced in the reaction
mixture at a rate of 30 parts per hour over 2 hours.
The resultant reaction solution was slowly poured into
10 4000 parts of water and then, subjected to filtration
and water-washing to obtain 196.6 parts of crude green
pigment 2. The crude green pigment 2 thus obtained was
found to consist of 58.0% of crude halogenated copper
phthalocyanine pigment and 42.0% of crude halogenated
15 aluminum phthalocyanine pigment, wherein the crude
halogenated copper phthalocyanine pigment contained in
its each molecule bromine atom and chlorine atom in
average number of 13.5 and 2.5, respectively, whereas
the crude halogenated aluminum phthalocyanine pigment
20 contained in its each molecule bromine atom and
chlorine atom in average number of 13.5 and 2.5,
respectively.

<Crude green pigment 3>

65 parts of aluminum phthalocyanine were dissolved
25 in a fused salt mixture which was heated in advance to
140°C, the fused salt mixture comprising 429 parts of
aluminum chloride and 96 parts of sodium chloride,

thereby obtaining a mixture, which was then stirred for 2 hours while maintaining the aforementioned temperature. Then, the reaction temperature of the mixture was increased to 180°C, and bromine was added dropwise in the reaction mixture at a rate of 48 parts per hour over 5 hours. Subsequently, chlorine was introduced in the reaction mixture at a rate of 30 parts per hour over 2 hours. The resultant reaction solution was slowly poured into 4000 parts of water and then, subjected to filtration and water-washing to obtain 193.5 parts of crude green pigment 3. The crude green pigment 3 thus obtained was found to consist only of crude halogenated aluminum phthalocyanine pigment, wherein the crude halogenated aluminum phthalocyanine pigment contained in its each molecule bromine atom and chlorine atom in average number of 13.5 and 2.5, respectively.

<Crude green pigment 4>

65 parts of copper phthalocyanine were dissolved in a fused salt mixture which was heated in advance to 130°C, the fused salt mixture comprising 429 parts of aluminum chloride and 96 parts of sodium chloride, thereby obtaining a mixture, which was then stirred for 2 hours while maintaining the aforementioned temperature. Then, the reaction temperature of the mixture was increased to 180°C, and bromine was added dropwise in the reaction mixture at a rate of 48 parts

per hour over 5 hours. Subsequently, chlorine was introduced in the reaction mixture at a rate of 30 parts per hour over 2 hours. The resultant reaction solution was slowly poured into 4000 parts of water and then, subjected to filtration and water-washing to obtain 193.5 parts of crude green pigment 4. The crude green pigment 4 thus obtained was found to consist of 97% of crude halogenated copper phthalocyanine pigment and 3% of crude halogenated aluminum phthalocyanine pigment, wherein the crude halogenated copper phthalocyanine pigment contained in its each molecule bromine atom and chlorine atom in average number of 13.5 and 2.5, respectively, whereas the crude halogenated aluminum phthalocyanine pigment contained in its each molecule bromine atom and chlorine atom in average number of 13.5 and 2.5, respectively.

<Crude green pigment 5>

225 parts of biphenyl, 45 parts of naphthalene, 128 parts of phthalodinitrile, 48 parts of titanium tetrachloride and 2 parts of pyridine were mixed together, and heated to a temperature of 200°C to allow a reaction to take place, which was followed by the filtration, drying and pulverization to obtain crude titanium phthalocyanine. Then, 200 parts of aluminum chloride and 40 parts of sodium chloride were heated to 120°C to obtain an eutectic salt, and 40 parts of crude titanium phthalocyanine was added to the eutectic salt

to obtain a mixture, which was then stirred for
30 minutes. Then, the reaction temperature of mixture
was increased to 180°C, and bromine was added dropwise
in the reaction mixture at a rate of 30 parts per hour
5 over 5 hours. Subsequently, chlorine was introduced in
the reaction mixture at a rate of 20 parts per hour
over 2 hours. The resultant reaction solution was
slowly poured into 2500 parts of water and then,
subjected to filtration and water-washing to obtain a
10 crude green pigment 5. The crude green pigment 5 thus
obtained was found to consist of 58.0% of crude
halogenated titanium phthalocyanine pigment and 42.0%
of crude halogenated aluminum phthalocyanine pigment,
wherein the crude halogenated titanium phthalocyanine
15 pigment contained in its each molecule bromine atom and
chlorine atom in average number of 13.5 and 2.5,
respectively, whereas the crude halogenated aluminum
phthalocyanine pigment contained in its each molecule
bromine atom and chlorine atom in average number of
20 13.5 and 2.5, respectively.

<Crude green pigment 6>

20 parts of copper phthalocyanine were dissolved
in a fused salt mixture which was heated in advance to
150°C, the fused salt mixture comprising 80 parts of
25 aluminum chloride, 10 parts of sodium chloride and
10 parts of sodium sulfate, thereby obtaining a
mixture. Then, the reaction temperature of the mixture

was increased to 160°C, and bromine was added dropwise in the reaction mixture at a rate of 7.4 parts per hour over 6 hours. Subsequently, the resultant reaction mixture was heated up to 180°C, and then, chlorine was introduced in the reaction mixture at a rate of 4 parts per hour over 5 hours. The resultant reaction solution was slowly poured into 1000 parts of water and then, subjected to filtration and water-washing to obtain 45.4 parts of crude green pigment 6. The crude green pigment 6 thus obtained was found to consist of 99.9% of crude halogenated copper phthalocyanine pigment and 0.1% of crude halogenated aluminum phthalocyanine pigment, wherein the crude halogenated copper phthalocyanine pigment contained in its each molecule bromine atom and chlorine atom in average number of 13.5 and 2.5, respectively, whereas the crude halogenated aluminum phthalocyanine pigment contained in its each molecule bromine atom and chlorine atom in average number of 13.5 and 2.5, respectively.

Then, the crude green pigments were subjected to a pigmentization processing according to the following methods to manufacture green pigments.

<Green pigment 1>

500 parts of the crude green pigment 4, 500 parts of sodium chloride and 250 parts of diethylene glycol were charged in a 1-gallon stainless steel kneader (Inoue Manufacturing Co., Ltd.) and were kneaded for

4 hours at a temperature of 120°C. Then, this kneaded mixture was cast in 5L of hot water and heated at a temperature of 70°C for one hour with stirring to obtain a slurry product, which was repeatedly subjected to filtration and water-washing to remove sodium chloride and diethylene glycol. The resultant product thus obtained was dried a whole day and night at a temperature of 80°C to obtain 490 parts of green pigment 1. By the way, the green pigment 1 was found to consist of 97% of halogenated copper phthalocyanine pigment and 3% of halogenated aluminum phthalocyanine pigment.

<Green pigment 2>

345 parts of the crude green pigment 4, 155 parts of the crude green pigment 1, 500 parts of sodium chloride and 250 parts of diethylene glycol were charged in a 1-gallon stainless steel kneader (Inoue Manufacturing Co., Ltd.) and were kneaded for 4 hours at a temperature of 120°C. Then, this kneaded mixture was cast in 5L of hot water and heated at a temperature of 70°C for one hour with stirring to obtain a slurry product, which was repeatedly subjected to filtration and water-washing to remove sodium chloride and diethylene glycol. The resultant product thus obtained was dried a whole day and night at a temperature of 80°C to obtain 490 parts of green pigment 2. By the way, the green pigment 2 was found to consist of 95% of

halogenated copper phthalocyanine pigment and 5% of
halogenated aluminum phthalocyanine pigment.

<Green pigment 3>

5 500 parts of the crude green pigment 1, 500 parts
of sodium chloride and 250 parts of diethylene glycol
were charged in a 1-gallon stainless steel kneader and
were subjected to the same procedures as those of the
green pigment 1, thereby obtaining 490 parts of green
pigment 3. By the way, the green pigment 3 was found
10 to consist of 90.5% of halogenated copper
phthalocyanine pigment and 9.5% of halogenated aluminum
phthalocyanine pigment.

<Green pigment 4>

15 282 parts of the crude green pigment 4, 218 parts
of the crude green pigment 2, 500 parts of sodium
chloride and 250 parts of diethylene glycol were
charged in a 1-gallon stainless steel kneader and were
subjected to the same procedures as those of the green
pigment 1, thereby obtaining 490 parts of green pigment
20 4. By the way, the green pigment 4 was found to
consist of 79.0% of halogenated copper phthalocyanine
pigment and 21.0% of halogenated aluminum
phthalocyanine pigment.

<Green pigment 5>

25 154 parts of the crude green pigment 4, 346 parts
of the crude green pigment 2, 500 parts of sodium
chloride and 250 parts of diethylene glycol were

charged in a 1-gallon stainless steel kneader and were subjected to the same procedures as those of the green pigment 1, thereby obtaining 490 parts of green pigment 5. By the way, the green pigment 5 was found to consist of 70.0% of halogenated copper phthalocyanine pigment and 30.0% of halogenated aluminum phthalocyanine pigment.

<Green pigment 6>

500 parts of the crude green pigment 2, 500 parts of sodium chloride and 250 parts of diethylene glycol were charged in a 1-gallon stainless steel kneader and were subjected to the same procedures as those of the green pigment 1, thereby obtaining 490 parts of green pigment 6. By the way, the green pigment 6 was found to consist of 58.0% of halogenated copper phthalocyanine pigment and 42.0% of halogenated aluminum phthalocyanine pigment.

<Green pigment 7>

410 parts of the crude green pigment 4, 90 parts of the crude green pigment 5, 500 parts of sodium chloride and 250 parts of diethylene glycol were charged in a 1-gallon stainless steel kneader and were subjected to the same procedures as those of the green pigment 1, thereby obtaining 490 parts of green pigment 7. By the way, the green pigment 7 was found to consist of 79.5% of halogenated copper phthalocyanine pigment, 10.0% of halogenated aluminum phthalocyanine

pigment and 10.5% of halogenated titanium
phthalocyanine pigment.

<Green pigment 8>

5 500 parts of the crude green pigment 6, 500 parts
of sodium chloride and 250 parts of diethylene glycol
were charged in a 1-gallon stainless steel kneader and
were subjected to the same procedures as those of the
green pigment 1, thereby obtaining 490 parts of green
10 pigment 8. By the way, the green pigment 8 was found
to consist of 99.9% of halogenated copper
phthalocyanine pigment and 0.1% of halogenated aluminum
phthalocyanine pigment.

<Green pigment 9>

15 450 parts of the crude green pigment 3, 50 parts
of the crude green pigment 6, 500 parts of sodium
chloride and 250 parts of diethylene glycol were
charged in a 1-gallon stainless steel kneader and were
subjected to the same procedures as those of the green
pigment 1, thereby obtaining 490 parts of green pigment
20 9. By the way, the green pigment 9 was found to
consist of 9.9% of halogenated copper phthalocyanine
pigment and 90.1% of halogenated aluminum
phthalocyanine pigment.

25 Then, by making use of these green pigments, green
photosensitive colored compositions (resist materials)
were manufactured, wherein the mixing ratio between the
halogenated copper phthalocyanine pigment and the

second halogenated metallophthalocyanine pigment was altered.

Example 1

A mixture having the following composition was stirred to form a uniform dispersion, which was filtered using a 1 μ m filter to prepare an alkali development type photosensitive colored composition.

Green pigment 1	4.5 parts
Acrylic resin solution	24.0 parts
Trimethylol propane triacrylate ("NK ester ATMPT", Shin-Nakamura Chemical Co., Ltd.)	5.4 parts
Photo-initiator ("Irgacure 907", Ciba-Geigy Co., Ltd.)	0.3 part
Sensitizer ("EAB-F", Hodogaya Chemical Co., Ltd.)	0.2 part
Cyclohexanone	65.1 parts

Examples 2 to 7

Alkali development type photosensitive colored compositions were prepared in the same manner as that set forth in Example 1 except that the green pigments 2 to 7 were respectively substituted for the green pigment 1.

Comparative Example 1

An alkali development type photosensitive colored composition was prepared in the same manner as that set forth in Example 1 except that the green pigment 8 was substituted for the green pigment 1.

Comparative Example 2

An alkali development type photosensitive colored

composition was prepared in the same manner as that set forth in Example 1 except that the green pigment 9 was substituted for the green pigment 1.

5 The photosensitive colored compositions obtained in Examples 1 to 7, and Comparative Examples 1 and 2 were respectively coated on the surface of glass substrate 100 mm × 100 mm and 1.1 mm in thickness by making use of a spin coater at a revolving speed of 500 rpm, 1000 rpm, 1500 rpm or 2000 rpm to thereby
10 obtain four kinds of coated substrate, each differing in film thickness. Then, after being dried at a temperature of 70°C for 20 minutes, the coated film was exposed to ultraviolet ray at an integrated quantity of light of 150 mJ by means of ultra-high pressure mercury
15 lamp. Thereafter, the coated substrate was heated for one hour at a temperature of 230°C, and, after being allowed to cool, the chromaticity (Y, x, y) of the resultant green coated film where the C-light source was employed was measured by means of
20 microspectrophotometer ("OSP-SP100"; Olympus Kogaku Co., Ltd.). Based on the results obtained through the measurements on the chromaticity-spectrometry of four groups of sample, the maximum transmittance (Tmax), x and y at the moment when the minimum value of spectral
25 transmittance of the wavelength ranging from 400 to 700 nm became 1% were determined. Further, the features of surface of the substrate where the coating

was performed at a revolving speed of 1000 rpm was observed by means of an optical microscope ("BX60"; Olympus Kogaku Co., Ltd.). The results thus obtained are shown in Table 1.

5

Table 1

Colored composi- tion	Y	x	y	Tmax	Tmin	Surface State
Example 1	64.21	0.2526	0.4679	90.7%	1.0%	○*
Example 2	65.32	0.2541	0.4563	91.3%	1.0%	○
Example 3	66.75	0.2572	0.4433	91.8%	1.0%	○
Example 4	67.75	0.2626	0.4444	92.2%	1.0%	○
Example 5	69.12	0.2665	0.4416	92.2%	1.0%	○
Example 6	70.38	0.2714	0.4427	92.4%	1.0%	○
Example 7	66.82	0.2584	0.4434	91.8%	1.0%	○
Comp. Ex. 1	62.53	0.2501	0.4797	90.5%	1.0%	○
Comp. Ex. 2	67.22	0.3169	0.4175	77.2%	1.0%	○

*) The mark "○" indicates that the surface state was excellent.

10

As shown in Table 1, all of the green coated films which were obtained by making use of the colored composition of the present invention were found as having an increased brightness "Y" under the conditions where the chromaticity "x" thereof was within the range of 0.25 to 0.34, and the chromaticity "y" thereof was within the range of 0.43 to 0.58. It will be also seen from Table 1 that the brightness of the green coated films according to the present invention was enhanced

15

as the content of halogenated aluminum phthalocyanine pigment was increased as far as the content of halogenated aluminum phthalocyanine pigment was limited within the range of not more than 80 mol%. Whereas, the green coated film of Comparative Example 1 where the content of halogenated aluminum phthalocyanine pigment was 0.1%, i.e. smaller than the range defined by the present invention was found lower in brightness. Further, the green coated film of Comparative Example 2 where the content of halogenated aluminum phthalocyanine pigment was 90%, i.e. larger than the range defined by the present invention, was found insufficient in concentration of color in greenness in view of a relatively small "y" value of 0.4175, thereby making it unsuitable for use as a green filter segment, even though the brightness "Y" thereof was as large as 67.

Next, for the adjustment of color tone, a green pigment and a yellow pigment (C.I. Pigment Yellow 150) were combined to prepare a green photosensitive colored composition (resist material).

Example 8

A mixture having the following composition was stirred to form a uniform dispersion, which was filtered using a 1 μ m filter to prepare an alkali development type photosensitive colored composition.

Green pigment 1	3.6 parts
-----------------	-----------

	Yellow pigment (PY150)	0.9 parts
	Acrylic resin solution	24.0 parts
5	Trimethylol propane triacrylate ("NK ester ATMPT", Shin-Nakamura Chemical Co., Ltd.)	5.4 parts
	Photo-initiator ("Irgacure 907", Ciba-Geigy Co., Ltd.)	0.3 part
10	Sensitizer ("EAB-F", Hodogaya Chemical Co., Ltd.)	0.2 part
15	Cyclohexanone	65.1 parts

Examples 9 to 13

Alkali development type photosensitive colored compositions were prepared in the same manner as that set forth in Example 8 except that the kind of green pigment as well as the mixing ratio (weight ratio) between the green pigment and the yellow pigment were altered as described in the following Table 2.

The photosensitive colored compositions obtained in Examples 8 to 13 were respectively coated on the surface of glass substrate 100 mm × 100 mm and 1.1 mm in thickness by making use of a spin coater so as to obtain a film thickness exhibiting $x = 0.3172$, and $y = 0.4703$. Then, after being dried at a temperature of 70°C for 20 minutes, the coated film was exposed to ultraviolet ray at an integrated quantity of light of 150 mJ by means of ultra-high pressure mercury lamp. Thereafter, the coated substrate was heated for one hour at a temperature of 230°C, and, after being allowed to cool, the brightness (Y), maximum transmittance (Tmax), minimum transmittance (Tmin) and contrast of

the resultant green coated film where the D65-light
source was employed were measured by means of
microspectrophotometer ("OSP SP100"; Olympus Kogaku
Co., Ltd.). Further, the features of surface of the
5 substrate was observed by means of an optical
microscope ("BX60"; Olympus Kogaku Co., Ltd.). The
results thus obtained are shown in Table 2.

TOP SECRET

Table 2

Colored composition	Green Pigment	Green pigment/ Yellow pigment	Y	Tmax	Tmin	Contrast	Surface state
Example 8	Pigment 1	75/25	79.03	94.37%	15.60%	1880	○*
Example 9	Pigment 2	76/24	79.34	94.28%	15.32%	1920	○
Example 10	Pigment 3	78/22	79.95	94.66%	15.02%	1970	○
Example 11	Pigment 4	82/18	80.34	94.44%	14.66%	2010	○
Example 12	Pigment 5	85/15	80.76	94.43%	13.45%	2050	○
Example 13	Pigment 6	87/13	80.54	94.40%	11.44%	2110	○

*) The mark "○" indicates that the surface state was excellent.

As shown in Table 2, all of the green coated films which were obtained by making use of the colored composition of the present invention were found as having an increased brightness as the content of halogenated aluminum phthalocyanine pigment was increased even if the "x" and "y" (hue) thereof was adjusted by making use of the yellow pigment. It will be also seen from Table 2 that as far as the content of halogenated aluminum phthalocyanine pigment was limited within the range of not more than 80 mol%, the content of the yellow pigment to be employed for the adjustment of color tone could be reduced as the content of halogenated aluminum phthalocyanine pigment was increased, and at the same time, the contrast of tone was enabled to enhance as the content of halogenated aluminum phthalocyanine pigment was increased.

Next, in the same manner as in the case of the aforementioned green photosensitive colored compositions, a blue photosensitive colored composition and a red photosensitive colored composition were prepared. Then, by making use of these two kinds of colored compositions and the green photosensitive colored compositions which were obtained in Examples 1 to 13, color filters was manufactured according to the following method.

<Blue photosensitive colored composition>

Blue pigment: C.I. Pigment Blue 15:6 ("Lionol Blue ES", Toyo Ink Mfg. Co., Ltd.) 4.5 parts

	Acrylic resin solution	24.0 parts
5	Trimethylolpropane triacrylate ("NK ester ATMPT", Shin-Nakamura Chemical Co., Ltd.)	5.4 parts
	Photo-initiator ("Irgacure 907", Ciba-Geigy Co., Ltd.)	0.3 part
10	Sensitizer ("EAB-F", Hodogaya Chemical Co., Ltd.)	0.2 part
	Cyclohexanone	65.1 parts
15	<Red photosensitive colored composition>	
	Red pigment: C.I. Pigment Red 254 ("Irga for Red B-CF", Ciba-Geigy Co., Ltd.)	4.0 parts
20	Red pigment (C.I. Pigment Red 177) ("Chromophthal Red A2B", Ciba-Geigy Co., Ltd.)	0.5 parts
	Acrylic resin solution	24.0 parts
25	Trimethylol propane triacrylate ("NK ester ATMPT", Shin-Nakamura Chemical Co., Ltd.)	5.4 parts
	Photo-initiator ("Irgacure 907", Ciba-Geigy Co., Ltd.)	0.3 part
30	Sensitizer ("EAB-F", Hodogaya Chemical Co., Ltd.)	0.2 part
	Cyclohexanone	65.1 parts
35	Each of these photosensitive colored compositions	
	was coated on the surface of a glass substrate by	
	making use of a spin coater, and then dried at a	
	temperature of 70°C by making use of a hot air oven for	
	20 minutes. Then, the coated layer was exposed to	
40	ultraviolet ray through a photomask having a stripe-	
	like openings each having a width of 100 μm.	
	Thereafter, the unexposed portion was washed away by	
	making use of a 5% aqueous solution of sodium	
	carbonate, after which the residual layer was baked at	

a temperature of 230°C for 30 minutes by using a hot air oven to obtain a color filter which was provided with a red filter segment, a blue filter segment and a green filter segment, each segment having a stripe pattern
5 100 μ m in line width.

The color filters thus prepared were all excellent in brightness of white color.

Since the colored composition according to the present invention comprises a halogenated copper
10 phthalocyanine pigment and a second halogenated metallophthalocyanine pigment at a specific mixing ratio, the transmitting wavelength region of the colored composition is enabled to shift toward a longer wavelength side, thereby making it possible to form a
15 green filter segment which is extremely high in brightness.

Since the color filter provided with a green filter segment that can be formed by using the colored composition according to the present invention is
20 capable of providing a color liquid crystal display device with not only a high brightness but also a high chromaticity, the color filter would be suited for use as a color separating color filter for a transmissive/reflective type color liquid display device as well as
25 for a solid state image sensor.